
Product Description

- An aggressive paint remover containing an acid accelerator
- Thick formulation designed for aggressive stripping and cling to vertical surfaces
- A special combination of patented ingredients providing superior performance while keeping it safe for the worker and the environment.
- Recommended for use on: polyurethane topcoats, polysulfide primers, solvent and water based epoxy primer, acrylic melamine basecoat and enamel, cationic epoxy E-coat, acrylic latex and alkyd enamel.
- Do not use S-553 on aluminum, brass, copper, bronze, tin, bare steel, or galvanized surfaces.

Physical Properties

- Appearance: Thick, White Emulsion
- pH 2.0
- Volatiles Weight 98.0 %
- Weight/gallon 8.68 Lb/gl (1040.57 G/l)
- VOC 4.36 Lb/gl (522.45 G/l)
- EPA Method 24 Yes
- Solubility Partially Soluble In Water
- Specific Gravity 1.041
- Flash Point >212 ° F (>100 ° C)
- Do not allow to freeze

General Application Instructions

- Used at 100% concentration, S-553 can be brush or spray applied.
- Recommended equipment: Safety glasses, rubber gloves, 30:1 air powered high pressure pump, Graco #421 spray tip with protective guard.
- Apply maximum possible film build and allow dwelling for approximately 1 - 2 hours.
- Agitate thoroughly after 45 minutes dwell time with scrub brush, squeegee, or scraper.
- S-553 should be used as a primary paint remover in areas where paint build up has occurred over time.
- Rinse with water or remove with squeegee and repeat as necessary to fully remove paint buildup.

Note: As with all chemicals, proper safety procedures should be adhered to at all times. Please review product Material Safety Data Sheet prior to working with any chemicals. Please contact your Gage Products Company representative for process specific application instructions.

The technical information and suggestions for use made herein are based on Gage Products Company's research and experience and are believed to be reliable. Such information and suggestions however, do not constitute a warranty.

Since Gage Products Company has no control over the conditions under which the product is transported, stored, handled, and/or applied, buyers must determine for themselves, by preliminary tests or otherwise, the suitability of the product for their purposes.
