

# 71553 GageSol® Paint Stripper

## PRODUCT DESCRIPTION

- ◆ A special combination of patented ingredients that provide superior performance while keeping the worker and environment safe.
- ◆ An effective paint remover which contains an acid accelerator
- ◆ A thick formulation designed for aggressive stripping and clinging to vertical surfaces
- ◆ Recommended for use on the following: polyurethane topcoats, polysulfide primers, solvent and water based epoxy primer, acrylic melamine basecoat and enamel, cationic epoxy E-coat, acrylic latex and alkyd enamel
- ◆ Do not use 71553 on aluminum, brass, copper, bronze, tin, bare steel, or galvanized surfaces

## PHYSICAL PROPERTIES

- ◆ Appearance: White, Multi-phase liquid
- ◆ pH: 2.0
- ◆ Weight/ Gallon: 8.68 lbs/gal (1040.57 g/l)
- ◆ VOC: 4.36 lbs/gal ( 522.45 g/l)
- ◆ Solubility: Partially Soluble In Water
- ◆ Specific Gravity: 1.0415
- ◆ Flash Point: >212 ° F (>100 ° C)
- ◆ Do not allow to freeze

## GENERAL APPLICATION INSTRUCTIONS

- ◆ Used at 100% concentration, 71553 can be applied with a brush or spray.
- ◆ 71553 should be used as a primary paint remover where paint build up has occurred over time.
- ◆ Recommended equipment: Safety glasses, rubber gloves, 30:1 air powered high pressure pump, Graco #421 spray tip with protective guard.
- ◆ Apply maximum possible film build, and let it settle for approximately 1 - 2 hours.
- ◆ Agitate thoroughly after 45 minutes resting time with a scrub brush, squeegee, or scraper.
- ◆ Rinse with water or remove with squeegee and repeat until paint buildup is removed.



*Note: As with all chemicals, proper safety procedures should be adhered to at all times. Please review product Safety Data Sheet prior to working with any chemicals. Please contact your Gage Products Company representative for process specific application instructions. The technical information and suggestions for use made herein are based on Gage Products Company's research and experience and are believed to be reliable. Such information and suggestions however, do not constitute a warranty. Since Gage Products Company has no control over the conditions under which the product is transported, stored, handled, and/or applied, buyers must determine for themselves, by preliminary tests or otherwise, the suitability of the product for their purposes.*